



MIRACHEM INDUSTRIES

B-310, Virwani Industrial Estate
Off Western Express Highway
Goregaon (East), Mumbai - 400 063, India
Tel.: +91 22 42417575 / 29271378
Fax: +91 22 42417550

www.mirachemindustries.com
Email:
admin@mirachemindustries.com
mirachem@bom5.vsnl.net.in
mirachemindustries@gmail.com

MIRAVYL - TL

Miravyl - TL is a versatile vinyl based resin compound specially designed to impart stiff feel and body to the textile fabrics.

- Imparts body and bulkiness without papery feel
- Gives stiffness with elastic handle
- May be used on sarees and other dress materials
- Finish is fast to washing
- Increases inter-yarn cohesion and acts as a non-slip finish to reduce thread slippage and fabric distortion in loosely woven material
- Easily dispersible in cold water
- Excellent conductivity, hence, most suitable for Autodosing finishing machines
- Does not cause coating over rolls due to use of heavy concentration during finishing (Lining cloth)
- Loading can be up to 200 gpl as against conventional product
- Most suitable for interlining coating
- No wastage due to adherence of the material to the transfer container (easily porable)

Properties:

Appearance	: White Liquid
Chemical Nature	: Aqueous dispersion of vinyl resin
Ionic Nature	: Nonionic
Solubility	: Dispersible
pH (2% solution)	: 5.0 ± 1.0
Stability	: Resist to Hard Water
Compatibility	: Compatible with all products used in finishing
Storage Stability	: Stable for 3 months if stored in a cool and dry place

Method of Application:

The dosage to be used for finishing depends upon the type of fabric and the finish desired.

In general, a dosage of 60 - 80 g/l **Miravyl - TL** may be used for obtaining a stiff finish on coarser to medium type fabrics alongwith required finishing auxiliaries.

General safety instructions

The usual hygiene and safety rules for handling chemicals should be observed in storage, handling and use. The product should not be swallowed. For further information, please consult existing safety data sheet.

Note :

The data contained in this communication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. Responsibility for compliance with the requirements of the downstream textile market rests with the textile processor.