



MIRACHEM INDUSTRIES

B-310, Virwani Industrial Estate
Off Western Express Highway
Goregaon (East), Mumbai - 400 063, India
Tel.: +91 22 42417575 / 29271378
Fax: +91 22 42417550

www.mirachemindustries.com
Email:
admin@mirachemindustries.com
mirachem@bom5.vsnl.net.in
mirachemindustries@gmail.com

MIRA - AMH

MIRA - AMH is a synthetic product for imparting full, firm and smooth handle, slip resistance and pilling resistance to all.

- **MIRA - AMH** is stable to high concentrations of metal ions and to mild acids and alkalis.
- **MIRA - AMH** when used along with wash and wear finishes, helps to get excellent control, by helping to get balanced firmness and smoothness.
- **MIRA - AMH** gives a full, firm and smooth handle to all kinds of fabric. It gives full handle without excessive stiffness, thus helping to achieve desired drape.
- **MIRA - AMH** is highly suitable to get excellent hand control for wash and wear finishing.
- **MIRA - AMH** does not cause yellowing, discolouration or mal-odour. It does not effect the whiteness of white goods.
- **MIRA - AMH** can be applied on a winch, jigger or padding mangle.

Properties: -

Appearance	: Colourless Viscous Liquid
Chemical Nature	: Acrylic copolymers
pH (2 % Solution)	: 7.5 - 8.5
Ionic Nature	: Anionic
Solubility	: Soluble
Compatibility	: Compatible with cationic, anionic and nonionic products
Stability	: Resist to hard water
Storage Stability	: Stable for 6 months if stored in a cool & dry place. (Not sensitive to frost)

Method of Applications:

MIRA - AMH is applied in the form of its aqueous solution. The goods are entered directly into the finishing bath, dried and cured.

1. For finishing of polyamide and polyester sarees, and dress materials.

	Pad with
MIRA - AMH	: 20.0 - 40.0 gpl
Tobler - CSI	: 20.0 gpl
Pick-up	: 2 dips / 2 nips (70% pick-up)
Dry	: at 100°C for 5 minutes



MIRACHEM INDUSTRIES

B-310, Virwani Industrial Estate
Off Western Express Highway
Goregaon (East), Mumbai - 400 063, India
Tel.: +91 22 42417575 / 29271378
Fax: +91 22 42417550

www.mirachemindustries.com
Email:
admin@mirachemindustries.com
mirachem@bom5.vsnl.net.in
mirachemindustries@gmail.com

2. For hand control on polyester/cotton and polyester/viscose and cottons.

Pad with

MIRA - AMH	: 20.0 - 40.0 gpl
Auxiset - V	: 60.0 - 80.0 gpl
Pick-up	: 2 dips / 2 nips (70% pick-up)
Dry	: 100°C for 5 minutes
Cure	: 150°C for 4 minutes

General safety instructions:

The usual hygiene and safety rules for handling chemicals should be observed in storage, handling and use.
The product should not be swallowed. For further information, please consult existing safety data sheet

Note :

The data contained in this communication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions drawings, photographs, data, proportions, weights, etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. Responsibility for compliance with the requirements of the downstream textile market rests with the textile processor.